

Uvijet OZ

UV Curing Ink System for the Inca Onset i-Series Printers

PRODUCT INFORMATION

The Uvijet OZ ink range is a high quality, UV curable inkjet system developed for the display POP and signage markets. The inks provide superior resistance to the post print processes printed items may require, such as cutting, creasing and routing.

Features

- Greater flexibility and reduced edge chipping
- Fast cure for high production output
- Ultra low print odour
- Wide adhesion range
- Recommended for both internal & external applications
- Suitable for decorating uneven surfaces
- 5 kilo open top containers for ease of use

Ink Properties

Using Fujifilm's unique Micro-V dispersion technology to maximise pigment loading, Uvijet OZ UV curing inks deliver vibrant, lightfast colours that last. The ink has been specially developed for the Inca Onset flatbed printers and offers superb dot reproduction and adhesion to a wide range of rigid and flexible uncoated materials.

Colour Range

OZ215 Cyan
 OZ867 Magenta Blue Shade
 OZ135 Magenta Pink Shade
 OZ052 Yellow
 OZ004 Black
 OZ255 Lt Cyan
 OZ185 Lt Magenta Pink Shade
 OZ335 Lt Magenta Blue Shade
 OZ021 White

Available in 5 kilo containers

QV017 UV Flush

Available in 1 and 5 litre containers

ZE680 Adhesion Promoter

ZE720 Adhesion Master

ZE700 Fusion Ultra

Available in 1 litre containers.

Application Range

Uvijet OZ has been designed to decorate a wide range of rigid and flexible materials including the following:

THE END USER MUST DETERMINE THE SUITABILITY OF THIS PRODUCT FOR THE INTENDED USE PRIOR TO PRODUCTION.

Media Type	Adhesion Characteristics*
Display Board	✓✓✓
Corrugated Board	✓✓✓
Foam Centred Board	✓✓✓
Foam PVC	✓✓✓
Acrylic	✓ (A) will improve adhesion to ✓✓✓
Flexible PVC	✓✓✓
Self-Adhesive PVC	✓✓✓
Gloss Rigid PVC	✓✓✓
Fluted Polypropylene	✓✓
Polyethylene	✓✓
Paper	✓✓✓
Polycarbonate	✓✓ (B) will improve adhesion to ✓✓✓
Polystyrene	✓✓
Polyester	✓✓
Digital Dibond	✓✓✓
Self-Cling	✓✓
Vinyl Banner	✓✓✓

Excellent ✓✓✓ **Good** ✓✓ **Fair** ✓

*Using Satin print modes

A = ZE680 Adhesion Promoter may optimise performance

B = ZE700 Fusion Ultra may optimise performance

Curing

Excellent cure and adhesion are achieved immediately on curing. However, maximum adhesion, chemical, scuff and scratch resistance may not be obtained until 24 hours after initial curing. The actual level of cure will depend upon ink thickness, substrate and the UV curing lamps being used. Superior through cure may be obtained by reducing the print speed to increase the overall UV dose.

Pre-production Tests

Uvijet OZ is formulated to adhere to most major brands of plastic, polypropylene, polyethylene and polystyrene materials with a surface energy level of 42 dynes/cm or higher.

Uvijet OZ inks have been formulated to withstand cutting, drilling or routing finishing processes. Such work should be conducted within 24 hours of being printed. However it is strongly recommended that all substrates are tested before proceeding with a commercial run.

Plastics

Certain plastics may be impregnated with lubricants which, like plasticisers, migrate impairing adhesion and block resistance for a considerable period after printing. This can be overcome by wiping the surface with isopropyl alcohol (IPA) before printing.

Chemical and Abrasion Resistance

Uvijet OZ inks have good chemical and excellent abrasion resistance. However, for optimum resistance over-vernishing with a durable UV screen varnish such as Uvibond UV383 is recommended.

Outdoor Use

Accelerated weathering tests have been carried out in a Xenon Arc Weatherometer set to the SAEJ1960 standard. Under these conditions the accelerated weathering of Uvijet OZ inks equates to approximately 24 months outdoor exposure in a temperate climate, such as the UK.

For polyethylene materials it is recommended that Uvijet Adhesion Master ZE720 is applied prior to printing to maximise ink and substrate adhesion.

Where prolonged outdoor use is required, it is strongly recommended to obtain verification of the actual durability of the material from the manufacturer or substrate supplier prior to use to ensure that the choice of material will not adversely effect the durability of Uvijet digital inks.

Storage

Uvijet OZ ink should not be stored in direct sunlight or near heat sources and should be kept away from peroxides. For optimum shelf-life, products should be stored at moderate temperatures between 5°C and 30°C.

When stored in a cool environment Uvijet OZ inks are expected to have a shelf-life of 12 months from date of manufacture.

Fujifilm Speciality Ink Systems Limited:

- Has certification to the International Environmental Standard, ISO 14001.

- Has certification to the Quality Management Standard, ISO 9001.
- Has certification to the Occupational Health and Safety Standard, ISO 18001.
- Is committed to minimising the risk to users of our products, and also to minimising the impact of our activities on the environment, from formulation through to production and supply.
- Research and development team, work to an in house Health Safety and Environmental policy, termed 'Design for Health, Safety and Environment', with the aim of proactively developing products with the least impact on health, safety and the environment.
- Regularly review and monitor our impacts and activities, setting objectives and targets as part of a continual improvement process.
- Is committed to reducing waste through better use of raw materials, energy, water, re-use and recycling.

Safety and Handling

Uvijet OZ Inks:

- Have a flash point greater than 55°C and are therefore not classified as 'dangerous substance' under the Dangerous Substances and Explosive Atmospheres Regulations (DSEAR).

Comprehensive information on the safety and handling of Uvijet inks is given in the appropriate Safety Data Sheets.

Environmental Information

Uvijet OZ Inks:

- Do not contain ozone-depleting chemicals as described in the Montreal Convention.
- Are formulated free from aromatic hydrocarbons.
- Are free from any volatile solvent and can therefore be considered to have less impact on the environment when compared to solvent-based products.

Uvijet Fusion Primers

ZE680 Adhesion Promoter & ZE700 Fusion Ultra:

- Do not contain ozone-depleting chemicals as described in the Montreal Convention.
- Are formulated free from aromatic hydrocarbons

ZE720 Adhesion Master:

- Does not contain ozone-depleting chemicals as described in the Montreal Convention.

The information and recommendations contained in this Product Information sheet, as well as technical advice otherwise given by representatives of Fujifilm Speciality Ink Systems Limited and its associated companies, whether verbally or in writing, are based on our present knowledge and believed to be accurate. However, no guarantee regarding their accuracy is given as we cannot cover or anticipate every possible application of our products and because manufacturing methods, printing stocks and other materials vary. For the same reason our products are sold without warranty and on condition that users shall make their own tests to satisfy themselves that they will meet fully their particular requirements. Our policy of continuous product improvement might make some of the information contained in this Product Information sheet out of date and users are requested to ensure that they follow current recommendations.

FUJIFILM SPECIALITY INK SYSTEMS LIMITED

Pysons Road, Broadstairs
Kent CT10 2LE
United Kingdom
T: +44 (0)1843 866668
F: +44 (0)1843 872184
www.fujifilm.eu