

Product Information Bulletin

Fujicolor Crystal Archive

Professional Paper Super Type P



1. Features and uses

FUJICOLOR CRYSTAL ARCHIVE PAPER SUPER TYPE P is a silver halide color paper designed exclusively for digital output. When used in conjunction with medium or large scale digital printer systems or the FUJIFILM FRONTIER DIGITAL MINILAB, this paper yields high image quality digital prints that make it suitable for professional uses such as portrait or commercial photography.

Features

- | | |
|------------------------------------|--|
| • Purer Whiteness | Clearer, more distinct print images and sharper text quality |
| • Vibrant Color Reproduction | Expanded color reproduction range with high color saturation, ideally suited to commercial use |
| • Excellent Latent Image Stability | Stable production of more uniform high quality prints for greater productivity |
| • Excellent Image Stability | High level of image stability ideal for display purposes |
| • Professional base paper | Thicker more durable base with a professional water mark and strippable for canvas mounting |
| • High productivity | Realizes high productivity when used in conjunction with Frontier 5**/7** series |

2. Safelight

Handle in total darkness. If safelight use is unavoidable, observe the following precautions.

- Expose paper no longer than 1 minute to light emitted through two Fuji Safelight Filter No. 103A (or Wratten Safelight Filter No. 13) in a 10 watt tungsten lamp safelight located at least 1 meter from the work area
- Safelight filters fade with extended use and need regular checking. Replace when paper fogging is detected.
- Exposed paper is susceptible to safelight induced sensitivity increases in the exposed area. For this reason, exposed paper should be subjected as little as possible to safelight illumination.

3. Pre-processing paper handling / storage

The higher the temperature and humidity, the more paper, whether unused, unexposed or exposed, is susceptible to adverse changes in speed, color balance, physical characteristics and other properties. Unprocessed paper is best stored at low temperatures. Specifically, the following conditions should be used for paper storage.

- Short term storage: Store in a cool and dark location, away from direct sunlight, high temperature and high humidity
- Long term storage: Below 10°C (50°F)

Raw paper which has been stored at a low temperature (by refrigeration) should be set aside and allowed to warm to room temperature prior to being opened. If the paper is taken out of its packaging immediately after being removed from refrigerated storage, condensation will form on the paper surfaces, resulting in print color changes and easily damaged surfaces.

The shortest periods required to return freezer or refrigerator stored paper to room temperature (minimum temperature equalization periods) are as follows:

20°C (68°F) Temperature Equalization Periods

Unit: hours

| Storage Temperature | -20°C (-4°F) | 0°C (32°F) | 10°C (50°F) |
|-------------------------------------|-----------------|---------------|----------------|
| Paper Size | | | |
| 15.2cm x 175 m (6 in. x 575 ft.) | 9 | 7 | 5 |

- NOTES**
- Do not heat paper in order to equalize temperatures.
 - Remove paper from refrigeration one day before use.

If exposed paper remains unprocessed for extended periods of time under normal room conditions or is subjected to high temperature and/or high humidity, changes in the color balance and other properties may occur.

The time between exposure and development should be fixed in order to obtain consistent quality. Avoid waiting until the next day to develop the exposed paper. Rather than holding the paper for processing the next day, initiate processing as soon as possible.

4. Processing

This paper is designed for use with Fujicolor Paper Process, CP48S and CP49E or RA-4 type processes.

Combining this paper with Fujifilm chemicals results in many advantages including faster processing, greater processing stability, reduced contamination hazards, greater ease in solution preparation and higher print quality.

5. Control strips

Processing control can be provided through the use of FUJICOLOR CRYSTAL ARCHIVE PAPER Control Strips Process CP-40FA/43FA/47L/48S/49E.

6. Post-processing print handling / storage

Since prints are usually used for the long-term recording of images, as much effort as possible is made to use materials that exhibit the least amount of change over time. The effects of high force during folding, light, heat, oxygen in the air, contaminating gases, humidity and mold cannot be completely avoided. It is recommended to use low force during page folding for album assembly. Also the change in the photographic image or base material is minimized by maintaining the appropriate storage conditions for prints, such as those used by museums and art galleries. Temperature and humidity control is the most important key to minimizing the change that occurs in prints.

Prints stored in the dark under the following conditions may be expected to show almost no change over time:

| Storage period with almost no change | Temperature | Relative Humidity |
|--------------------------------------|----------------------|-------------------|
| More than 20 years | Below 10°C (50°F) | 30% — 50% |
| 10 — 20 years | Below 25°C (77°F) | 30% — 50% |

Notes on Prints Storage

- Prints should be inserted into albums, mounted, or placed into a bag (plastic*) for photographic prints before being stored.
- Even during normal storage, it is recommended that prints be stored in a place as free as possible from hot and humid conditions and away from direct illumination. The following are examples of undesirable storage conditions.

*Made of polyester, polystyrene or polypropylene plastic, etc.

- Storage in a room closet facing a wall exposed to cold outside air (which may cause condensation).
- Storage in a place near the ceiling, such as an attic, the top of a closet or cupboard (where high temperatures may occur).

- Storing prints with their front surfaces facing each other may result in unexpected problems. If the adjacent print placement is unavoidable, it is necessary to keep the surface separated by interleaving sheets of paper for example.

7. Light sources for viewing

When inspecting finished color prints, it is essential that an illumination source be used that has superior spectral characteristics, adequately high color temperature and sufficient brightness. Prints can appear different when viewed under different lighting conditions. For precise results, prints should be examined under the conditions designated by ISO 3664-2009. As a general guide, the following conditions are recommended.

Color Temperature : 5000 ± 300 K
Average Illumination : 500 Lux or more
General Color Rendering Index: Ra 90 or more*

* To attain these values, special fluorescent lamps designed for color evaluation (e.g. EDL type) should be used.


When inspecting finished prints, be careful to shut out all external light and colored reflected light.

8. Paper surface available

FUJICOLOR CRYSTAL ARCHIVE PAPER SUPER TYPE P is available in Lustre surface.

9. Markings (Box/Emulsion numbers)

9.1 Box markings



9.2 Bag labeling




9.3 Emulsion numbers

Emulsion numbering will be in ascending order from 5xx-xxx

Note: FUJICOLOR paper is marked with a three-digit emulsion number followed by an additional three digit roll number.

Should any problem arise with FUJICOLOR CRYSTAL ARCHIVE PAPER SUPER TYPE P, the additional three digit number suffix to the emulsion number should be indicated on the claim. Where possible also report the 10 digit production ID code on the label.

10. Back printing



11. Technologies incorporated in this paper


11.1 X-Coupler Technology

Through the incorporation of a cyan coupler (X-Coupler Technology), which features a molecular structure developed by Fujifilm's proprietary technologies, this paper is capable of reproducing the subtle shades of green and of forming colors of high purity, such as vibrant blues and reds.


11.2 NLS (New Low Stain Spectral Sensitizer) Technology and ARR (Advanced Resistance-to-Radiation) Technology

FUJICOLOR CRYSTAL ARCHIVE PAPER SUPER TYPE P has not only WE (White Enhancing) Technology but also incorporated NLS Technology, which is Fujifilm's LSS Technology taken to a higher level. The results are more brilliant, purer whites and clearer and more distinct highlights. In addition, ARR Technology, an advance over the previous RR Technology, has been incorporated to suppress color paper fogging caused by ambient radiation, enhancing the maintenance of white purity in unexposed color paper.

12. Spectral dye density curves




13. Spectral sensitivity curves



* Sensitivity equals the reciprocal of the exposure (J/cm²) requires to produce a specified density

14. Paper structure



15. Sizes available

| Crystal Archive Super Type P Paper | | |
|------------------------------------|-------|------|
| Widths \ Lengths | 275' | 575' |
| | 5 in. | |
| 6 in. | | L |
| 8 in. | | L |
| 10 in. | L | L |
| 10 in. Bulk | | L |
| 11 in. | L | |
| 12 in. | L | |

Note: Size availability can change without prior notice.

16. Calibration data

Fujicolor Crystal Archive Super Type P Paper

| Equipment | | Latest Software | Calibration data | | | |
|----------------|------------------------|-----------------|---|-------------------------------|-------------------|-----------|
| Brand | Name | | LUT + Target density RGB | Basic calibration ymcd | Intermittence rgb | Thickness |
| Frontier | 3 series | Installer R | LUT H | n.a. | n.a. | n.a. |
| | 5 series | Installer R | LUT H | | | |
| | 7 series | V 4.01 | LUT H-1 | | | |
| Noritsu | QSS 28 - LP24Pro | Vol.2 7.20 | 142 | n.a. | n.a. | n.a. |
| | QSS 35/37/38/39 series | Vol.3 N4.54 | | | | |
| Agfa Dlab | Dlab 1,2,3 | | 2.00 / 2.00 / 1.90 | 0.97 / 1.00 / 1.02 | | |
| KIS | DKS 15x, 16x, 17x | | Printer defines own and highest possible Dmax settings (exposure vs chemistry relation) | | | |
| ISAG | Fastprint | | 2.00 / 2.00 / 1.90 | n.a. | n.a. | 0.24 |
| | Wideprint 8", 12nG | | | | | |
| | Wideprint R2R | | 142 | n.a. | n.a. | n.a. |
| ZBE | SE, Pro Lab, R2R | | 2.00 / 2.00 / 1.90 | n.a. | n.a. | n.a. |
| Polieletronica | Laserlab 50/76/127 | | Printer defines own and highest possible Dmax settings (exposure vs chemistry relation) | | | |
| Durst | Epsilon | | 2.00 / 2.00 / 1.90 | 0.004 / 0.056 / 0.000 / 0.920 | 90 / 50 / 37 | n.a. |
| | Zeta | | | | | |
| | Theta 50/51 | | | 170.2 / 112.0 / 0.00 / 104.3 | | |
| | Theta 76/76HS | | | 0.006 / 0.085 / 0.000 / 1.325 | 101 / 56 / 42 | |
| | Lambda | | | 124.0 / 95.8 / 0.00 / 129.0 | | |

All recommended Dmax values can only be reached when using highly active chemistry equal to Fujifilm CPRA Digital Pro AC and Fujifilm ADM chemistry
For competitive and regenerated chemistry the Dmax should be reduced by -0.10 for all three colors.

17. Use with Frontier

Please refer to the following calibration data as a guide when using FUJICOLOR CRYSTAL ARCHIVE PAPER SUPER TYPE P on a digital printer.

All Frontiers requires a dedicated LUT when printing. It is necessary to adjust for the paper type for each paper magazine by changing the paper "Type" specification in the "Paper Magazine Registration" menu.

Registration and Setup of the Paper Type specification on Paper Magazine for Frontier 330/350/370/390 series

- Log in to the < 4 Setup and Maintenance > menu with < SE2 > for the user name and password of < 7777 >.
- Select < 5 Printer Adjustment / Maintenance >, < 1 Paper Magazine Registration > (Menu 451) and change the type to "H" as shown in the table below.

| Paper | Type | Surface |
|-------------------------------|------|---------|
| Crystal Archive Paper Type II | H | L |

- Select < 2 Print Condition Setup and Check >, < 1 Paper condition Setup > (menu 421) and perform a paper condition setup for all magazines for which the paper type is changed.

It is important to click the "initialize" button to initialize the settings before making the paper condition setup. After initialization the first paper condition setups will deviate by a great degree, but this will be balanced after the second or third attempt.

(Please note that clicking on the "initialize" button will not be possible if you do not log in with a user name or lab administrator account or higher).

Registration and Setup of the Paper Type specification on Paper Magazine for Frontier 340/355/375/550/570/590 series

- Log in to the < 4 Setup and Maintenance > menu with < SE2 > for the user name and password of < 7777 >.
- Select the < Adjustment / Maintenance >, < 02 Print Condition Setup and Check >, < 0221 Paper Magazine Registration >. Change the paper type

| Paper | Type | Surface |
|-------------------------------|------|---------|
| Crystal Archive Paper Type II | H | L |

to "H" as shown in the table below.

- Click the < Setup and Maintenance >, < 02 Print condition Setup and Check >, < 0200 Paper Condition Setup > and perform a paper condition setup for all magazines for which the paper type is changed.

It is important to click the "initialize" button to initialize the settings before making the paper condition setup. After initialization the first paper condition setups will deviate by a great degree, but this will be balanced after the second or third attempt.

(Please note that clicking the "initialize" button will not be possible if you do not log in with a user name of lab administrator or higher)

Registration and Setup of the Paper Type specification on Paper Magazine for Frontier 700 series

1. On the Maintenance Application display, click the [maintenance] to access the Maintenance display. Click [Extension] – [Setup] – [Laser Setup] – [Paper Specification Registration/Setup].

2. Select the paper type “H-1” as shown in table below:


| Paper | Type | Surface |
|-------------------------------|------|---------|
| Crystal Archive Paper TYPE II | H-1 | L |

Follow the instructions on the Paper Specification registration / set up. Make the test prints and register the measurement results.

18. Technical Support

In case abnormalities are found when using this FUJICOLOR CRYSTAL ARCHIVE PAPER SUPER TYPE P please contact your local Fujifilm subsidiary and/or distributor.

Relevant Fujifilm subsidiary and/or distributor contact information can be found on the following internet address: <http://www.fujifilm.com/worldwide/>

| | | |
|---|--|--|
| Notice: The data herein published were derived from materials taken from general production runs. However changes in specification may occur without notice | | |
|  | FUJIFILM NORTH AMERICA CORPORATION 200 Summit Drive Valhalla, NY 10595 | ©Technical Market Support November 2018 Document nr: AF3-0257U |