

# Product Information Bulletin

## Fujicolor Crystal Archive Paper Supreme



### 1. Features and uses

FUJICOLOR CRYSTAL ARCHIVE PAPER SUPREME is a silver halide color paper designed to produce high image quality color prints on both analog and digital printers. It incorporates silver halide emulsion technology, coupler technology and layer design technology to deliver enhanced color reproduction, white purity, image stability and handling. Furthermore, when used in conjunction with the Frontier 5\*\*/7\*\* series it enables the realization of superfast processing, resulting in a drastic improvement in productivity.

FUJICOLOR CRYSTAL ARCHIVE PAPER SUPREME is provided with a thicker base and is recognized by its attractive golden back print.

#### Features

- |  |  |
|--|--|
| • More Vivid Color Reproduction                        | Retains beautiful colors such as subtle shades of green, vivid blues and reds  |
| • More Brilliant White plus Improved Highlight Details | Further improved whiteness, with clearer, more distinct highlight details.   |
| • Excellent Image Stability                            | Exhibits high image stability during long term dark storage and excellent light storage condition, as well as storability with respect to nitrogen oxide, ozone and other gases. |
| • Improved Handling Characteristic                     | Improved tolerances for processing unevenness and pressure induced density marks.  |
| • High productivity                                    | Realizes high productivity when used in conjunction with Frontier 5**/7**  |

### 2. Safelight

Handle in total darkness. If safelight use is unavoidable, observe the following precautions.

- Expose paper no longer than 1 minute to light emitted through two Fuji Safelight Filter No. 103A (or Wratten Safelight Filter No. 13) in a 10 watt tungsten lamp safelight located at least 1 meter from the work area.
- Safelight filters fade with extended use and need regular checking. Replace when paper fogging is detected.
- Exposed paper is susceptible to safelight induced sensitivity increases in the exposed area. For this reason, exposed paper should be subjected as little as possible to safelight illumination.

### 3. Pre-processing paper handling / storage

The higher the temperature and humidity, the more paper, whether unused, unexposed or exposed, is susceptible to adverse changes in speed, color balance, physical characteristics and other properties. Unprocessed paper is best stored at low temperatures. Specifically, the following conditions should be used for paper storage.

- Short term storage: Store in a cool and dark location, away from direct sunlight, high temperature and high humidity
- Long term storage: Below 10°C (50°F)

Raw paper which has been stored at a low temperature (by refrigeration) should be set aside and allowed to warm to room temperature prior to being opened. If the paper is taken out of its packaging immediately after being removed from refrigerated storage, condensation will be formed on the paper surfaces, resulting in print color changes and easily damaged surfaces.

The minimum temperature equalization periods are as follows:

## 20°C (68°F) Temperature Equalization Periods

Unit: hours

Storage Temperature Paper Size	-20°C (-4°F)	0°C (32°F)	10°C (50°F)
10.2cm x 186 m (4 in. x 610 ft.)	6	5	3.5

- NOTES**
- Do not heat paper in order to equalize temperatures.
  - Remove paper from refrigeration one day before use.

If exposed paper remains unprocessed for extended periods of time under normal room conditions or is subjected to high temperature and/or high humidity, changes in the color balance and other properties may occur. The time between exposure and development should be fixed in order to obtain consistent quality. Avoid waiting until the next day to develop the exposed paper. Rather than holding the paper for processing the next day, initiate processing as soon as possible.

### 4. Processing

This paper is designed for use with Fujicolor Paper Process, CP48S and CP49E or RA-4 type processes.

Combining this paper with Fuji chemicals results in many advantages including faster processing, greater processing stability, reduced contamination hazards, greater ease in solution preparation and higher print quality.

### 5. Control strips

Processing control can be provided through the use of FUJICOLOR CRYSTAL ARCHIVE PAPER Control Strips Process CP-40FA/43FA/47L/48S and 49E.

### 6. Post processing print handling / storage

Since prints are usually used for the long term recording of images, as much effort as possible is made to use materials that exhibit the least amount of change over time. But the effects of high force during folding, light, heat, oxygen in the air, contaminating gases, humidity and mold cannot be completely avoided. Also the change in the photographic image or base material is minimized by maintaining the appropriate storage conditions for prints, such as those used by museums and art galleries. Temperature and humidity control is the most important key to minimizing the change that occurs in prints. Prints stored in the dark under the following conditions may be expected to show almost no change over time.

Storage period with almost no change	Temperature	Relative Humidity
More than 20 years	Below 10°C (50°F)	30% — 50%
10 — 20 years	Below 25°C (77°F)	30% — 50%

### Notes on Prints Storage:

- Prints should be inserted into albums, mounted, or placed into a bag (plastic\*) for photographic prints before being stored.

\*Made of polyester, polystyrene or polypropylene plastic, etc.

- Even during normal storage, it is recommended that prints be stored at a place as free as possible from hot and humid conditions, and away from direct illumination. The following are examples of undesirable storage conditions.

- Storage in a room closet facing a wall exposed to cold outside air (which may cause condensation).
- Storage in a place near the ceiling, such as an attic, the top of a closet or cupboard (where high temperatures may occur).

- Storing prints with their front surfaces facing each other may result in unexpected problems. If the adjacent print placement is unavoidable, it is necessary to keep the surface separated by, for example, the use of interleaving sheets of paper.

### 7. Light sources for viewing

When inspecting finished color prints, it is essential that an illumination source be used that has superior spectral characteristics, adequately high color temperature and sufficient brightness. Prints can appear different when viewed under different lighting conditions. For precise results, prints should be examined under the conditions designated by ISO 3664-2009. As a general guide, the following conditions are recommended.

Color Temperature : 5000 ± 300 K  
 Average Illumination : 500 Lux or more  
 General Color Rendering Index: Ra 90 or more\*

\* To attain these values, special fluorescent lamps designed for color evaluation (e.g. EDL type) should be used.

When inspecting finished prints, be careful to shut out all external light and colored reflected light.

### 8. Paper surfaces available

FUJICOLOR CRYSTAL ARCHIVE PAPER SUPREME is available in Glossy or Lustre surface.

## 9. Back printing



## 10. Markings (Box/Emulsion numbers)

### 10.1 Box markings



“+” indication means that at least 1 spliced baby roll is packed

### 10.2 Bag labeling



“+” indication means that a splice is present in the baby roll.

### 10.3 Emulsion numbers

Emulsion numbering will be in ascending order from 7xx-xxx at introduction.


#### Note:

FUJICOLOR paper is marked with a three digit emulsion number followed by an additional three digit number which is provided for production control purposes only. Should any problem arise with FUJICOLOR CRYSTAL ARCHIVE PAPER SUPREME, the additional three digit number suffix to the emulsion number should be indicated on the claim.


## 11. Use with FA / FA compact

Since cyan forming dye has been modified in FUJICOLOR CRYSTAL ARCHIVE PAPER, a problem may arise when this paper is used on the printing condition settings made using the densitometer QT-600 built into Fuji Minilab FA/FA compact series. When FUJICOLOR CRYSTAL ARCHIVE PAPER SUPREME is used with Fuji Minilab FA/FA compact series of minilabs, it is necessary to set the printing conditions using the “ring around print” method or another densitometer.

## 12. Spectral dye density curves




## 13. Spectral sensitivity curves



\* Sensitivity equals the reciprocal of the exposure ( $\mu\text{cm}^2$ ) required to produce a specified density

## 14. Paper structure



## 15. Sizes available

### Crystal Archive Supreme Paper

Widths \ Lengths	Lengths	
	275'	575'
4 in		G,L
5 in.		G,L
6 in.		G,L
8 in.	G,L	G,L
10 in.	G,L	G,L
12 in.	L	

**Note:** Size availability may change without prior notice. Availability depends on surface and may vary by market.

## 16. Calibration data

### Fujicolor Crystal Archive Supreme Paper

Equipment		Latest Software	Calibration data			
Brand	Name		LUT + Target density RGB	Basic calibration ymcd	Intermittence rgb	Thickness
Frontier	3 series	Installer R	LUT H, surface selection	n.a.	n.a.	n.a.
	5 series	Installer R	LUT H, surface selection			
	7 series	V 4.01	LUT H-1			
Noritsu	QSS 28 - LP24Pro	Vol.2 7.20	142	n.a.	n.a.	n.a.
	QSS 35/37/38/39 series	Vol.3 N4.54				
Agfa Dlab	Dlab 1,2,3		2.00 /2.00 / 1.95	0.97 / 1.00 / 1.02		
KIS	DKS 15x, 16x, 17x		Printer defines own and highest possible Dmax settings (exposure vs chemistry relation)			
ISAG	Fastprint		2.00 /2.00 / 1.95	n.a.	n.a.	0.23
	Wideprint 8", 12nG		142	n.a.	n.a.	n.a.
	Wideprint R2R					
ZBE	SE, Pro Lab, R2R		2.00 /2.00 / 1.95	n.a.	n.a.	n.a.
Polelectronica	Laserlab 50/76/127		Printer defines own and highest possible Dmax settings (exposure vs chemistry relation)			
Durst	Epsilon		2.00 /2.00 / 1.95	0.004 /0.056 / 0.000 / 0.920	90 / 50 / 37	n.a.
	Zeta					
	Theta 50/51			170.2 / 112.0 / 0.00 / 104.3		
	Theta 76/76HS			0.006 / 0.085 / 0.000 / 1.325	101 / 56 / 42	

All recommended Dmax values can only be reached when using high active chemistry equal to Fujifilm CPRA Digital Pro AC and Fujifilm ADM chemistry  
For competitive and regenerated chemistry the Dmax should be reduced with -0.10 in all three colors

## 17. Use with Frontier

Please refer to the following calibration data as a general guide when using FUJICOLOR CRYSTAL ARCHIVE PAPER SUPREME on a digital printer.

All Frontiers requires a dedicated LUT when printing. It is necessary to adjust for the paper type for each paper magazine by changing the paper "Type" specification in the "Paper Magazine Registration" menu.

### Registration and Setup of the Paper Type specification on Paper Magazine for Frontier 330/350/370/390 series

- Log in to the < 4 Setup and Maintenance > menu with < SE2 > for the user name and password of < 7777 >.
- Select < 5 Printer Adjustment / Maintenance >, < 1 Paper Magazine Registration > (Menu 451) and change the type to "H" as shown in the table below.

Paper	Type	Surface
Crystal Archive Type II	H	G / L

- Select < 2 Print Condition Setup and Check >, < 1 Paper condition Setup > (menu 421) and perform a paper condition setup for all magazines for which the paper type is changed.

It is important to click the "initialize" button to initialize the settings before making the paper condition setup. After initialization the first paper condition setups will deviate by a great degree, but this will be balanced after the second or third attempt.

(Please note that clicking on the "initialize" button will not be possible if you do not login with a user name or lab administrator account or higher).

### Registration and Setup of the Paper Type specification on Paper Magazine for Frontier 340/355/375/550/570/590 series

- Log in to the < 4 Setup and Maintenance > menu with < SE2 > for the user name and password of < 7777 >.
- Select the < Adjustment / Maintenance >, < 02 Print Condition Setup and Check >, < 0221 Paper Magazine Registration >. Change the paper type to "H" as shown in the table below.

Paper	Type	Surface
Crystal Archive Type II	H	G / L

- Click the < Setup and Maintenance >, < 02 Print condition Setup and Check >, < 0200 Paper Condition Setup > and perform a paper condition setup for all magazines for which the paper type is changed.

It is important to click the "initialize" button to initialize the settings before making the paper condition setup. After initialization the first paper condition setups will deviate by a great degree, but this will be balanced after the second or third attempt.

(Please note that clicking the "initialize" button will not be possible if you do not log in with a user name of lab administrator or higher)

### Registration and Setup of the Paper Type specification on Paper Magazine for Frontier 700 series

- On the Maintenance Application display, click the [maintenance] to access the Maintenance display. Click [Extension] – [Setup] – [Laser Setup] – [Paper Specification Registration/Setup].
- Select the paper type "H-1" as shown in table below:

Paper	Type	Surface
Crystal Archive Type II	H-1	G / L

Follow the instructions on the Paper Specification registration / set up. Make the test prints and register the measurement results.

## 18. Technical Support

In case abnormalities are found when using this FUJICOLOR CRYSTAL ARCHIVE PAPER SUPREME please contact your local Fujifilm subsidiary and/or distributor.

Relevant Fujifilm subsidiary and/or distributor contact information can be found on the following internet address:  
<http://www.fujifilm.com/worldwide/>

**Notice:** The data herein published were derived from materials taken from general production runs. However changes in specification may occur without notice

**FUJIFILM**

FUJIFILM North America Corporation  
 200 Summit Lake Drive  
 Valhalla, NY 10595

©**Technical Market Support**  
 November 2018  
**Document nr:** AF3-0254U